

**HEAD OFFICE:**

Plot No. – 12, Sector B1,  
Local Shopping Complex, Vasant Kunj,  
New Delhi - 110 070 (INDIA).  
Tel: 0091-11-26139256 – 265  
Fax: 0091-11-26125739  
Web site: www.jindalpoly.com

**TECHNICAL SPECIFICATION SHEET (J-533/J-534)**

**DESCRIPTION:** J533/J534\* is corona treated; Co extruded standard clear film having excellent surface, good clarity, superior gloss and good handling property

**APPLICATIONS:** High clarity film suitable for Metallization, holographic, high quality lamination, and other industrial and general-purpose application.

**SALIENT FEATURES:**

- High clarity and transparency
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

<b>TECHNICAL DATA</b>						
Properties	Test method	Unit	J-533/J-534*			
<b>PHYSICAL</b>						
Thickness	ASTM D-374	Micron (Gauge)	75 (300)	100 (400)	125 (500)	
Yield	JPFTM	m <sup>2</sup> /kg (in <sup>2</sup> /lb)	9.5 (6680)	7.1(4990)	5.7 (4000)	
<b>OPTICAL</b>						
Haze	ASTM D-1003	%	2.0	2.2	2.5	
Total luminous transmittance	ASTM D-1003	%	89	89	89	
<b>MECHANICAL</b>						
Tensile strength (Min)	MD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1700 (24200)	1700 (24200)	1700 (24200)
	TD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1700 (24200)	1700 (24200)	1700 (24200)
Elongation (Min)	MD	ASTM D-882	%	120	120	120
	TD	ASTM D-882	%	100	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.45	0.45	0.45
	Dy	ASTM D-1894	-	0.35	0.35	0.35
<b>THERMAL</b>						
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5	1.5
<b>SURFACE</b>						
Wetting tension (Min) (Treated side)	ASTM D-2578	Dyne / cm	54	54	54	
<b>Electrical</b>						
Volume Resistivity	ASTM D-256	Ohm cm	10 <sup>16</sup>	10 <sup>16</sup>	10 <sup>16</sup>	


- **J-533: Treated surface wound inside, J-534: Treated surface wound outside**

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

**WORKS:**

28 - KM, Stone, Nashik - Igatpuri Road,  
Village : Mundegaon, Maharashtra  
Phone : + 91 2553 229100, 231002 / 3 / 5  
Fax: + 91 2553 231004



**HEAD OFFICE:**

Plot No. – 12, Sector B1,  
Local Shopping Complex, Vasant Kunj,  
New Delhi - 110 070 (INDIA).  
Tel: 0091-11-26139256 – 265  
Fax: 0091-11-26125739  
Web site: www.jindalpoly.com

**TECHNICAL SPECIFICATION SHEET (J-533/J-534)**

**DESCRIPTION:** J533/J534\* is corona treated; Co extruded standard clear film having excellent surface, good clarity, superior gloss and good handling property

**APPLICATIONS:** High clarity film suitable for Metallization, holographic, high quality lamination, and other industrial and general application.

**SALIENT FEATURES:**

- High clarity and transparency
- High surface gloss
- Excellent Machinability
- Excellent Mechanical Properties
- Excellent Dimensional Stability

<b>TECHNICAL DATA</b>					
Properties	Test method	Unit	J-533/J-534*		
<b>PHYSICAL</b>					
Thickness	ASTM D-374	Micron (Gauge)	175 (700)	250 (1000)	
Yield	JPFTM	m <sup>2</sup> /kg (in <sup>2</sup> /lb)	4.1 (2880)	2.9 (2040)	
<b>OPTICAL</b>					
Haze	ASTM D-1003	%	3.0	4.5	
Total luminous transmittance	ASTM D-1003	%	89	89	
<b>MECHANICAL</b>					
Tensile strength (Min)	MD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1700 (24200)	1600 (22800)
	TD	ASTM D-882	Kg/cm <sup>2</sup> (psi)	1700 (24200)	1600 (22800)
Elongation (Min)	MD	ASTM D-882	%	120	120
	TD	ASTM D-882	%	100	100
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894	-	0.45	0.45
	Dy	ASTM D-1894	-	0.35	0.35
<b>THERMAL</b>					
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.5	2.5
	TD	ASTM D-1204	%	1.5	1.5
<b>SURFACE</b>					
Wetting tension (Min) (Treated side)	ASTM D-2578	Dyne / cm	54	54	
<b>Electrical</b>					
Volume Resistivity	ASTM D-256	Ohm cm	10 <sup>16</sup>	10 <sup>16</sup>	

- **J-533: Treated surface wound inside, J-534: Treated surface wound outside**

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

**WORKS:**

28 - KM, Stone, Nashik - Igatpuri Road,  
Village : Mundegaon, Maharashtra  
Phone : + 91 2553 229100, 231002 / 3 / 5  
Fax: + 91 2553 231004

